

082520

CPI / DERWENT

9-27516B 5141

SU77 436891 770103

Steam hardening building material - contg. lime,
dehydrated clay powder and sand, used for casting wall,
heat insulating etc. units

IW - STEAM HARDEN BUILD MATERIAL CONTAIN LIME DEHYDRATE CLAY
POWDER SAND CAST WALL HEAT INSULATE UNIT

IN - KRZHEMINSK S A; VARLAMOV V P

PA - (BUIL-R) BUILDING MAT CONS

PN - SU607813 A 780425 DW7914 000pp

ORD - 1978-04-25

IC - C04B15/06

FS - CPI

DC - L02

AB - SU-607813 The compressive strength of the building
articles is improved, when the starting mixt. contains
(in wt.%) lime (I) 10-30, dehydrated, finely ground
clay (II) 20-50 and sand (III) the rest.
- The articles are prep'd. by forming and steaming for 12
hrs. at 97 degrees C.